

ELGILOY Specialty Metals – Strip Products

Hastelloy® alloy C-276

UNS N10276
W.Nr 2.4819

Hastelloy® alloy C-276 is a Nickel-Molybdenum-Chromium corrosion resistant alloy. The alloy is resistant to pitting, crevice corrosion, and stress corrosion cracking. Hastelloy® C-276 is hardened only by cold-working. Hastelloy® C-276 can operate from cryogenic temperatures up to 750°F (400°C).

Applications include springs, heat exchangers bellows and seals.

Industries supplied include: Chemical Processing, Pollution Control, Pulp and Paper Production, and Waste Treatment.

Nominal Composition

	Mo	Cr	Fe	W	Co	C	Si	Mn	V	P	S	Ni
min	15.0	14.5	4.0	3.0								Remainder
max	17.0	16.5	7.0	4.5	2.5	0.010	0.08	1.0	0.35	0.04	0.03	

Physical Properties

	At 70°F	At 20°C
Density	0.321 lb/in ³	8.89 g/cm ³
Modulus of Elasticity (E)	29.7x 10 ³ ksi	205 GPa
Modulus of Rigidity (G)	11.5x 10 ³ ksi	79.0 GPa
Coefficient of Expansion	6.78 microinches/in.-°F (70-600°F)	12.2 μm/m-°C (20-300°C)
Electrical Resistivity	51 μ ohm.in	130 μ ohm.cm
Thermal Conductivity	68.0 Btu-in./ft. ² hr.-°F	9.80 W/m-K

Applicable Specifications

Strip and Foil	ASTM B575, ASTM B906, ISO 6208, DIN 17750
----------------	---

Typical Mechanical Properties

Condition	Heat Treatment	Tensile Strength	Suggested Operating Conditions
Annealed	2050°F (1121°C)	120 – 160 Ksi (830 – 1100 MPa)	-300°F to 750°F (-184°C to 400°C)
Spring Temper		200 – 240 ksi (1380 – 1655 MPa)	-300°F to 750°F (-184°C to 400°C)

Hastelloy® is a registered trademark of Haynes International, Inc.

For further information Contact:
Email: Einfo@ELGILOY.COM
Phone: 1.888.843.2350

Elgiloy Specialty Metals - Strip Products
 1565 Fleetwood Dr.
 Elgin, IL 60123 USA

WWW.ELGILOY.COM