

## Specialty Metals – Strip Products

## Incoloy® Alloy 800

**UNS N08800** W.Nr 1.4876

Incoloy® Alloy 800 is used for its corrosion resistance, heat resistance, strength, and stability at high temperatures. It offers general corrosion resistance to many aqueous media and resists stress corrosion cracking. At elevated temperatures it resists oxidation, carburization, and sulfidation along with maintaining good rupture and creep strength. Applications include furnace components and equipment, petrochemical furnace cracker tubes, pigtails and headers, sheathes for electrical heating elements, stream generator tubing, and domestic appliances.

| Industries supplied include: Chemical, thermal, and food processing, and nuclear.        |           |           |                 |                    |   |       |                      |      |                 |                                       |     |  |  |
|--|-----------|-----------|-----------------|--------------------|---|-------|----------------------|------|-----------------|---------------------------------------|-----|--|--|
| Nominal Composition  |           |           |                 |                    |   |       |                      |      |                 |                                       |     |  |  |
|  | С         | Mn        | Si              | P                  | S   | Cr    | Ni                   | Ti   | Al              | Cu                                    | Fe  |  |  |
| min  | -         | -         | -               | -                  | -   | 19.00 | 30.00                | 0.15 | 0.15            | -                                     | -   |  |  |
| max  | 0.10      | 1.50      | 1.00            | 0.035              | 0.015                                     | 23.00 | 35.00                | 0.60 | 0.60            | 0.75                                  | Bal |  |  |
| Physical Properties  |           |           |                 |                    |   |       |                      |      |                 |                                       |     |  |  |
|  |           |           |                 |                    | At 70°F                                   |       |                      |      |                 | At 20°C                               |     |  |  |
| Density  |           |           |                 |                    | 0.287 lb/in <sup>3</sup>                  |       |                      |      |                 | 7.94 g/cm <sup>3</sup>                |     |  |  |
| Modulus of Elasticity (E)  |           |           |                 |                    | 28.50 x 10 <sup>3</sup> ksi               |       |                      |      |                 | 197 GPa                               |     |  |  |
| Modulus of Rigidity (G)  |           |           |                 |                    | 11 x 10³ ksi                              |       |                      |      |                 | 76 GPa                                |     |  |  |
| Coefficient of Expansion   |           |           |                 |                    | 9.4 microinches/in°F (70-1000°F)          |       |                      |      |                 | 16.8 μm/m-°C (20-538°C)               |     |  |  |
| Electrical Resistivity   |           |           |                 |                    | 38.9 μ ohm.in                             |       |                      |      |                 | 98.9 μ ohm.cm                         |     |  |  |
| Thermal Conductivity   |           |           |                 |                    | 80 Btu-in./ft.²hr°F                       |       |                      |      |                 | 11.5 W/m-K                            |     |  |  |
| Applicable Specifications  |           |           |                 |                    |   |       |                      |      |                 |                                       |     |  |  |
| Strip  |           |           |                 |                    | AMS 5871, ASTM A240, ASTM B409            |       |                      |      |                 |                                       |     |  |  |
| Typical Mechanical Properties – Spring Applications                                      |           |           |                 |                    |   |       |                      |      |                 |                                       |     |  |  |
| Condition  |           |           | Heat Treatment  |                    |   |       | Tensile Strength     |      |                 | Suggested Operating<br>Conditions     |     |  |  |
| Annealed   |           |           | 1900°F (1036°C) |                    |   |       | 75 ksi (520 MPa) min |      |                 | -300°F to 1500°F (-184°C<br>to 816°C) |     |  |  |
| INCOLOY® is a registered trademark of the Special Metals Corporation group of companies. |           |           |                 |                    |   |       |                      |      |                 |                                       |     |  |  |
| For fur  | ther info | rmation ( | Contact:        |                    | Elgiloy Specialty Metals - Strip Products |       |                      |      |                 |                                       |     |  |  |
| Email: Einfo@ELGILOY.COM   |           |           |                 | 1565 Fleetwood Dr. |   |       |                      |      | WWW.ELGILOY.COM |                                       |     |  |  |
| Phone: 1.888.843.2350  |           |           |                 |                    | Elgin, IL 60123 USA                       |       |                      |      |                 |                                       |     |  |  |