



Elgiloy Specialty Metals – Strip Products

Alloy 2507 Stainless Steel

UNS S32750
W. Nr 1.4410

Applicable Specifications

Strip and Foil | ASTM A240, NACE MR0175/ISO 15156

Description: Alloy 2507 is a super-duplex (austenitic/ferritic) stainless steel designed for applications which require exceptional strength and corrosion resistance surpassing that of 304 and 316 stainless steels. The alloy has excellent resistance to stress corrosion cracking as well as pitting, crevice, and erosion corrosion. Alloy 2507 also has high thermal conductivity, a low coefficient of thermal expansion, and good weldability.

Applications include: Desalination equipment, Saltwater handling, Flue gas desulfurization, Food processing equipment, Heat exchangers, Pulp mill bleach systems, and Oil distillation

Industries supplied include: Chemical Processing, Food Processing, Oil & Gas, and Power Generation

Nominal Composition

	C	Si	Mn	P	S	Cr	Ni	Mo	N	Cu
min	-	-	-	-	-	24.0	6.0	3.0	0.24	-
max	0.030	0.80	1.20	0.035	0.020	26.0	8.0	5.0	0.32	0.50

Physical Properties

	At 70°F	At 20°C
Density	0.280 lb/in ³	7.8 g/cm ³
Modulus of Elasticity (E)	29.0 x 10 ³ ksi	200 GPa
Modulus of Rigidity (G)	10.9 x 10 ³ ksi	75 GPa
Coefficient of Expansion	7.2 µin/in-°F (70-212°F)	12.96 µm/m-°C (20-100°C)
Electrical Resistivity	32.7 µohm-in	83.0 µohm-cm
Thermal Conductivity	118 Btu-in/ft ² -hr-°F	17.0 W/m-°C

Typical Mechanical Properties

Condition	Heat Treatment	Tensile Strength	Suggested Operating Conditions
Annealed	1920-2100°F (1050-1150°C)	1150-145 ksi (800-1000 MPa)	-58°F to 572°F (-50°C to 300°C)

Limitation of Liability and Disclaimer of Warranty:

- The content in these data sheets is provided primarily by third-party melting mills and is provided for reference only. It is not intended for engineering or design.
- Applications may be discussed, however, Elgiloy Specialty Metals, a Division of Combined Metals of Chicago L.L.C., does not recommend or endorse any material for any particular end use or application.
- The data included in this data sheet are typical values and may vary.
- Elgiloy Specialty Metals, a Division of Combined Metals of Chicago L.L.C., makes no representations or warranties, express or implied, as to the accuracy, completeness, condition, suitability, performance, fitness for a particular purpose, or merchantability of any information contained in any data sheet.
- In no event will Elgiloy Specialty Metals, a Division of Combined Metals of Chicago L.L.C., be liable for any damages whatsoever arising from the use of the information included in the data sheets.

For further information:
Email: stripinquiries@elgiloy.com
Phone: 1-888-843-2350

Elgiloy Specialty Metals - Strip Products
1565 Fleetwood Dr.
Elgin, IL 60123 USA

www.elgiloy.com

Rev Date: 8/26/2020