



# Elgiloy Specialty Metals – Strip Products

## 316/316L Stainless Steel

UNS S31600/S31603  
W. Nr 1.4401/1.4404

### Applicable Specifications

Strip and Foil AMS 5907, AMS 5524, ASTM F899, ASTM A666, NACE MR0175/ISO 15156

**Description:** 316 is an austenitic chromium-nickel-stainless steel containing molybdenum. This addition increases general corrosion resistance, improves resistance to pitting from chloride ion solutions, and provides increased strength at elevated temperatures. Properties are similar to those of Type 304/304L except that this alloy is somewhat stronger at elevated temperatures. Corrosion resistance is improved, particularly against sulfuric, hydrochloric, acetic, formic and tartaric acids; acid sulfates and alkaline chlorides. Type 316L is an extra-low carbon version of Type 316 that minimizes harmful carbide precipitation during welding.

**Applications include:** Exhaust manifolds, Furnace parts, Heat exchangers, Jet engine parts, Pharmaceutical and photographic equipment, Valve and pump trim, Tubing, Chemical equipment, Digesters, Tanks, Evaporators, Paper and textile processing equipment, Food processing equipment, and Marine parts.

**Industries supplied include:** Aerospace, Chemical Processing, Food Processing, Power Generation, General Manufacturing

### Nominal Composition

	C	Mn	Si	S	P	Ni	Cr	Mo	N	Fe
min	-	-	-	-	-	10.5	16.5	2.00	-	Bal
max	0.07	2.00	1.00	0.030	0.045	13.5	18.0	2.50	0.10	-

### Physical Properties

	At 70°F	At 20°C
Density	0.285 lb/in <sup>3</sup>	8.00 g/cm <sup>3</sup>
Modulus of Elasticity (E)	28.0 x 10 <sup>3</sup> ksi	193 GPa
Modulus of Rigidity (G)	10.1 x 10 <sup>3</sup> ksi	70 GPa
Coefficient of Expansion	9.2 μin/in-°F (70-212°F)	16.6 μm/m-°C (20-100°C)
Electrical Resistivity	29.1 μohm-in	74.0 μohm-cm
Thermal Conductivity	9.4 Btu-in/ft <sup>2</sup> -hr-°F (212°F)	16.2 W/m-°C (100°C)

### Typical Mechanical Properties

Condition	Heat Treatment	Tensile Strength	Suggested Operating Conditions
Annealed	1900-2050°F (1038-1121°C)	75-105 ksi (515-725 MPa)	-200°F to 1700°F (-184°C to 927°C)
¼ Hard ½ Hard Spring Temper	(Stress relieve 600-900°F as needed)	125 ksi min (860 MPa) 150 ksi min (1030 MPa) 185 ksi min (1275 MPa)	-200°F to 550°F (-184°C to 288°C)

#### Limitation of Liability and Disclaimer of Warranty:

- The content in these data sheets is provided primarily by third-party melting mills and is provided for reference only. It is not intended for engineering or design.
- Applications may be discussed, however, Elgiloy Specialty Metals, a Division of Combined Metals of Chicago L.L.C., does not recommend or endorse any material for any particular end use or application.
- The data included in this data sheet are typical values and may vary.
- Elgiloy Specialty Metals, a Division of Combined Metals of Chicago L.L.C., makes no representations or warranties, express or implied, as to the accuracy, completeness, condition, suitability, performance, fitness for a particular purpose, or merchantability of any information contained in any data sheet.
- In no event will Elgiloy Specialty Metals, a Division of Combined Metals of Chicago L.L.C., be liable for any damages whatsoever arising from the use of the information included in the data sheets.

For further information:  
Email: [stripinquiries@elgiloy.com](mailto:stripinquiries@elgiloy.com)  
Phone: 1-888-843-2350

Elgiloy Specialty Metals - Strip Products  
1565 Fleetwood Dr.  
Elgin, IL 60123 USA

[www.elgiloy.com](http://www.elgiloy.com)

Rev Date: 8/25/2020