

ELGILOY SPECIALTY METALS HIGH PERFORMANCE ALLOYS - WIRE DIVISION

EPCRA Notification pursuant to Section 313 or per 40 CFR Part 372

| ALLOY | Type | NOMINAL COMPOSITION | | | | | | BAL % Estimate | UNS NUMBER |
|---------------------------|------|----------------------|------|-------|------|--------|----------------------|----------------|------------|
| | | 313 Listed Chemicals | | | | | | BAL | UNS NUMBER |
| | | Ni | Co | Cr | Mn | Cu | Other | | |
| 25 - 6MO | 256M | 25 | - | 20 | 2 | 1 | N-.2 | - | N08926 |
| A-286® | A286 | 25.5 | - | 14.75 | 2 | - | V-.3 | - | S66286 |
| AL6XN® | AL6X | 24.5 | - | 21.00 | 2 | 0.750 | N-.215 | - | N08367 |
| ALLOY 20 (20Cb3) | AL20 | 35 | - | 20 | 2 | 3.500 | Cb-8*C-1.0 | - | N08020 |
| ELGILOY® | ELGI | 15 | 40 | 20 | 2 | - | Be-0.0100 | - | R30003 |
| HASTELLOY® B- 3 | HAB3 | 65 | 3 | 2 | 3 | - | V-.2 | - | N10675 |
| HASTELLOY C- 2000 | C200 | 59 | 2 | 23 | 0.5 | 1.600 | - | - | N06200 |
| HASTELLOY C- 22 | HC22 | 56 | 2.5 | 21.25 | 0.5 | - | V-.35, | - | N06022 |
| HASTELLOY C- 276 | C276 | 57 | 2.5 | 15.50 | 1 | - | V-.35 | - | N10276 |
| HASTELLOY C- 4 | HC4 | 65 | 2 | 16.00 | 1 | - | - | - | N06455 |
| HASTELLOY X | HASX | 47 | 1.5 | 21.75 | 1 | - | - | - | N06002 |
| HAYNES® 188 | H188 | 22 | 39 | 22 | 1.25 | - | La-.09 | - | R30188 |
| HAYNES 214 | H214 | 75 | 2 | 16 | 1 | - | Y-.021, Zr-.02 | - | N07214 |
| HAYNES 230 | H230 | 57 | 5 | 22 | 0.65 | - | La-.03 | - | N06230 |
| HAYNES 242 | H242 | 65 | 1 | 8 | 0.8 | 0.500 | - | - | N10242 |
| HAYNES 263 | H263 | 52 | 20 | 20 | 0.6 | 0.200 | - | - | N07263 |
| HAYNES 282 | H282 | BAL | 10 | 20 | 0.3 | 0.1 | Nb-.2, Ta-.1, Zr-.02 | 54.9185 | N07208 |
| INCOLOY® 825 | I825 | 42 | - | 21.50 | 1 | 2.250 | - | - | N08825 |
| INCOLOY 925 | I925 | 44 | - | 21 | 1 | 2.25 | Nb-.5 | - | N09925 |
| INCONEL® 600 | I600 | 72 | 1 | 15.50 | 1 | 0.500 | - | - | N06600 |
| INCONEL 601 | I601 | 60.5 | - | 23 | 1 | - | - | - | N06601 |
| INCONEL 625 | I625 | 58 | 1 | 21.50 | 0.5 | - | Nb-3.65 | - | N06625 |
| INCONEL 718 | I718 | 52.5 | 1 | 19 | 0.35 | - | Nb-5.125 | - | N07718 |
| INCONEL X - 750 | I750 | 70 | 1 | 15.50 | 0.35 | 0.500 | Cb+Ta- 1.05 | - | N07750 |
| L605 (HAYNES 25) | L605 | 10 | 51 | 20 | 1.5 | - | - | - | R30605 |
| MONEL® 400 | M400 | 66.5 | - | - | 2 | 31.000 | - | - | N04400 |
| MONEL K500 | M500 | 66.5 | - | - | 1.5 | BAL | - | 25.915 | N05500 |
| MP35N® | MP35 | 35 | 35 | 20 | 0.15 | - | - | - | R30035 |
| NI SPAN C® 902 | NISP | 42.250 | - | 5.325 | 0.8 | - | - | - | N09902 |
| NIMONIC® 90 | NM90 | 53 | 18 | 19.50 | 1 | - | - | - | N07090 |
| NITRONIC® 32 (XM - 28) | NI32 | 1.5 | - | 17.75 | 12.5 | - | N-.325 | - | S24100 |
| NITRONIC 50 (XM - 19) | NI50 | 12.5 | - | 22 | 5 | - | V-.2, Cb-.2 | - | S20910 |
| RENE 41 | RE41 | 58 | 11 | 19 | 0.1 | 0.500 | - | - | N07041 |
| Stainless Steel 17 - 7 PH | 177 | 7.125 | - | 17 | 1 | - | - | - | S17700 |
| Stainless Steel 316 | 316 | 12 | - | 17 | 2 | - | - | - | S31600 |
| Stainless Steel 316L | 316L | 12 | - | 17 | 2 | - | - | - | S31603 |
| Stainless Steel 321 | 321 | 10.5 | - | 18 | 2 | - | N-.1 | - | S32100 |
| Stainless Steel 347 | 347 | 10.5 | - | 18 | 2 | - | Nb-.9 | - | S34700 |
| WASPALLOY | WASP | 58 | 13.5 | 19.50 | 1 | - | Zr- .07 | - | N07001 |

Last Updated - 12/04/2020