

Alloy 2205 Stainless Steel

UNS S32205
W. Nr 1.4462

Applicable Specifications

Strip and Foil ASTM A240, NACE MR0175/ISO 15156

Description: Alloy 2205 is a duplex (austenitic/ferritic) stainless steel alloyed with chromium, molybdenum, and nitrogen for improved performance and corrosion resistance compared to 304 and 316 stainless steels. The alloy's distributed austenite/ferrite microstructure combined with the alloying additions provide resistance to stress corrosion cracking, pitting, and chlorine induced crevice corrosion. Alloy 2205 also has acceptable oxidation resistance up to 980°C, but only for specific applications as the material can become embrittled when exposed to temperatures between 300°C and 1000°C for extended periods.

Applications include: Mixing tanks, Heat exchangers, Pressure vessels, Extraction/distillation columns, Pulp processing equipment, Pipes, Pumps, Food processing equipment, Springs

Industries supplied include: Chemical Processing, Oil & Gas, Nuclear Power Generation, Food Processing

Nominal Composition

	C	Mn	P	S	Si	Ni	Cr	Mo	N	Fe
min	-	-	-	-	-	4.5	22.0	3	0.14	Bal
max	0.03	2.0	0.03	0.02	1.0	6.5	23.0	3.5	0.20	-

Physical Properties

	At 70°F	At 20°C
Density	0.284 lb/in ³	7.86 g/cm ³
Modulus of Elasticity (E)	29.0 x 10 ³ ksi	200 GPa
Coefficient of Expansion	11.1 µin/in-°F (70-2000°F)	14.0 µm/m-°C (0-300°C)
Electrical Resistivity	33.5 µohm-in	85.1 µohm-cm
Thermal Conductivity	104 Btu-in/ft ² -hr-°F	15.0 W/m-°C

Typical Mechanical Properties

Condition	Heat Treatment	Tensile Strength	Suggested Operating Conditions
Annealed	1868-2050°F (1020-1121°C)	120-150 ksi (825-1035 MPa)	-58°F to 572°F (-50°C to 300°C)
Spring Temper	(Stress relieve as needed)	200 ksi min (1380 MPa)	Up to 550°F (288°C)

Elgiloy Specialty Metals - Strip Products

1565 Fleetwood Dr.
Elgin, IL 60123 USA

Phone: 1-888-843-2350

www.elgiloy.com

LIMITATION OF LIABILITY AND DISCLAIMER OF WARRANTY:

The content in these data sheets is provided primarily by third-party melting mills and is provided for reference only. It is not intended for engineering or design.

Applications may be discussed, however, Elgiloy Specialty Metals does not recommend or endorse any material for any particular end use or application.

The data included in this data sheet are typical values and may vary.

Elgiloy Specialty Metals makes no representations or warranties, express or implied, as to the accuracy, completeness, condition, suitability, performance, fitness for a particular purpose, or merchantability of any information contained in any data sheet.

In no event will Elgiloy Specialty Metals be liable for any damages whatsoever arising from the use of the information included in the data sheets.