

AL-6XN® alloy

UNS N08367

Applicable Specifications

Strip and Foil | ASTM B688, ASTM A240

Description: AL-6XN® alloy is a corrosion resistant iron-base super-austenitic stainless steel specifically designed for seawater resistance. The alloy surpasses the performance of conventional duplex stainless steels and can be a lower-cost alternative than other nickel-base alloys. AL-6XN® also has resistance to a wide range of other corrosive environments, including protection from chloride induced stress corrosion cracking and pitting/crevice corrosion in oxidizing solutions.

Applications include: Mixing tanks, Heat exchangers, Extraction/distillation columns, Pipes, Pumps, Food processing equipment, Caustic chloride systems

Industries supplied include: Chemical Processing, Oil & Gas, Nuclear Power Generation, Food Processing

Nominal Composition

	C	Mn	P	S	Si	Ni	Cr	Mo	N	Cu	Fe
min	-	-	-	-	-	23.5	20.00	6.00	0.18	-	Bal
max	0.030	2.00	0.040	0.030	1.00	25.5	22.00	7.00	0.25	0.75	-

Physical Properties

	At 70°F	At 20°C
Density	0.291 lb/in ³	8.06 g/cm ³
Modulus of Elasticity (E)	28.3 x 10 ³ ksi	195 GPa
Modulus of Rigidity (G)	10.8 x 10 ³ ksi	74 GPa
Coefficient of Expansion	7.9 µin/in-°F (70-212°F)	14.2 µm/m-°C (20-100°C)
Electrical Resistivity	35 µohm-in	89.0 µohm-cm
Thermal Conductivity	7.5 Btu-in/ft ² -hr-°F	14.1 W/m-°C

Typical Mechanical Properties

Condition	Heat Treatment	Tensile Strength	Suggested Operating Conditions
Annealed	2030-2192°F (1110-1200°C)	100-130 ksi (690-900 MPa)	-320°F to 800°F (-196°C to 427°C)

AL-6XN® is a registered trademark of ATI Properties, Inc.

Elgiloy Specialty Metals - Strip Products
1565 Fleetwood Dr.
Elgin, IL 60123 USA

Phone: 1-888-843-2350

www.elgiloy.com

LIMITATION OF LIABILITY AND DISCLAIMER OF WARRANTY:

The content in these data sheets is provided primarily by third-party melting mills and is provided for reference only. It is not intended for engineering or design.

Applications may be discussed, however, Elgiloy Specialty Metals does not recommend or endorse any material for any particular end use or application.

The data included in this data sheet are typical values and may vary.

Elgiloy Specialty Metals makes no representations or warranties, express or implied, as to the accuracy, completeness, condition, suitability, performance, fitness for a particular purpose, or merchantability of any information contained in any data sheet.

In no event will Elgiloy Specialty Metals be liable for any damages whatsoever arising from the use of the information included in the data sheets.