



Specialty Metals – Strip Products

Hastelloy® B-3 alloy

UNS N10675
W. Nr 2.4600

HASTELLOY® B-3 alloy is a nickel-molybdenum alloy with thermal stability greater than that of Hastelloy B-2. It has excellent resistance to pitting, corrosion, and stress corrosion cracking. It has excellent resistance to hydrochloric acid at all concentrations and temperatures. It also withstands sulfuric, acetic, formic, and phosphoric acids, and other non-oxidizing media.

Applications include: chemical processing, vacuum furnaces, mechanical components.

Nominal Composition

	C	Mn	Si	P	S	Cr	Co	Mo	V	Fe	Al	W	Ni
min	-	-	-	-	-	1.00	-	27.00	-	1.00	-	-	65.00
max	0.01	3.00	0.10	0.030	0.010	3.00	3.00	32.00	0.20	3.00	0.50	3.00	-

Physical Properties

	At 70°F	At 20°C
Density	0.333 lb/in ³	9.22 g/cm ³
Modulus of Elasticity (E)	31.4 x 10 ³ ksi	216 GPa
Modulus of Rigidity (G)	12.0 x 10 ³ ksi	83 GPa
Coefficient of Expansion	6.6 microinches/in.-°F (70-1000°F)	11.8 μm/m-°C (20-538°C)
Electrical Resistivity	53.8 μ ohm.in	137 μ ohm.cm
Thermal Conductivity	78 Btu-in./ft. ² hr.-°F	11.2 W/m-K

Applicable Specifications

Strip	ASTM B333
-------	-----------

Typical Mechanical Properties – Spring Applications

Condition	Heat Treatment	Tensile Strength	Suggested Operating Conditions
Annealed	2100°F (1150°C)	110 ksi (760 MPa) min 125 ksi (860 MPA) typ	-300°F to 1800°F (-184°C to 900°C)

Hastelloy® is a registered trademark of Haynes International, Inc.

Elgiloy Specialty Metals - Strip
Products

Phone: 1.888.843.2350

1565 Fleetwood Dr.
Elgin, IL 60123 USA

WWW.ELGILOY.COM

LIMITATION OF LIABILITY AND DISCLAIMER OF WARRANTY:

The content in these data sheets is provided primarily by third-party melting mills and is provided for reference only. It is not intended for engineering or design.

Applications may be discussed, however, Elgiloy Specialty Metals does not recommend or endorse any material for any particular end use or application.

The data included in this data sheet are typical values and may vary.

Elgiloy Specialty Metals makes no representations or warranties, express or implied, as to the accuracy, completeness, condition, suitability, performance, fitness for a particular purpose, or merchantability of any information contained in any data sheet.

In no event will Elgiloy Specialty Metals be liable for any damages whatsoever arising from the use of the information included in the data sheets.