



# Specialty Metals – Strip Products

## Hastelloy® C-4 alloy

UNS N06455  
W. Nr 2.4610

HASTELLOY® C-4 alloy is a nickel-chromium-molybdenum alloy with excellent resistance to stress-corrosion cracking and to oxidizing atmospheres at high temperature. It has virtually the same corrosion resistance as C-276. It exhibits exceptional resistance to a wide variety of chemical process environments.

Applications include: Chemical processing, nuclear fuel processing, marine applications.

### Nominal Composition

	C	Mn	Si	P	S	Cr	Co	Mo	Ti	Fe	Al	W	Ni
min	-	-	-	-	-	14.00	-	14.00	-	-	-	-	
max	0.015	1.00	0.08	0.040	0.030	18.00	2.00	17.00	0.70	3.00	-	-	BAL

### Physical Properties

	At 70°F	At 20°C
Density	0.312 lb/in <sup>3</sup>	8.64 g/cm <sup>3</sup>
Modulus of Elasticity (E)	30.8 x 10 <sup>3</sup> ksi	211 GPa
Modulus of Rigidity (G)	11.4 x 10 <sup>3</sup> ksi	78.6 GPa
Coefficient of Expansion	7.4 microinches/in.-°F (70-1000°F)	13.3 μm/m-°C (20-538°C)
Electrical Resistivity	49.1 μ ohm.in	1.25 μ ohm.cm
Thermal Conductivity	70 Btu-in./ft. <sup>2</sup> hr.-°F	10.1 W/m-K

### Applicable Specifications

Strip	ASTM B575, NACE MR0175
-------	------------------------

### Typical Mechanical Properties – Spring Applications

Condition	Heat Treatment	Tensile Strength	Suggested Operating Conditions
Annealed	1950°F (1065°C)	100 ksi (690 MPa) min 125 ksi (860 MPA) typ	-300°F to 750°F (-184°C to 400°C)

Hastelloy® is a registered trademark of Haynes International, Inc.

Phone: 1.888.843.2350

Elgiloy Specialty Metals - Strip  
Products

1565 Fleetwood Dr.  
Elgin, IL 60123 USA

[WWW.ELGILOY.COM](http://WWW.ELGILOY.COM)

**LIMITATION OF LIABILITY AND DISCLAIMER OF WARRANTY:**

The content in these data sheets is provided primarily by third-party melting mills and is provided for reference only. It is not intended for engineering or design.

Applications may be discussed, however, Elgiloy Specialty Metals does not recommend or endorse any material for any particular end use or application.

The data included in this data sheet are typical values and may vary.

Elgiloy Specialty Metals makes no representations or warranties, express or implied, as to the accuracy, completeness, condition, suitability, performance, fitness for a particular purpose, or merchantability of any information contained in any data sheet.

In no event will Elgiloy Specialty Metals be liable for any damages whatsoever arising from the use of the information included in the data sheets.