

Hastelloy® alloy X

UNS N60002
W. Nr 2.4665

HASTELLOY® alloy X is a nickel-chromium-iron-molybdenum alloy that possesses an exceptional combination of oxidation resistance, fabricability and high-temperature strength. Alloy X exhibits good ductility after prolonged exposure to high temperatures.

Applications include: combustion chambers, gas turbine engine components such as honeycomb seals, compressor vanes and combustor cases.

Industries supplied include: Aerospace, industrial furnaces, petrochemical, and chemical processing.

Nominal Composition

	C	Mn	Si	P	S	Cr	Co	Mo	W	Fe	Al	Ti	Ni
min	0.05					20.50	0.50	8.00	0.20	17.00			
max	0.15	1.00	1.00	0.040	0.030	23.00	2.50	10.00	1.00	20.00	0.50	0.15	balance

Physical Properties

	At 70°F	At 20°C
Density	0.297 lb/in ³	8.22 g/cm ³
Modulus of Elasticity (E)	29.8 x 10 ³ ksi	205 GPa
Modulus of Rigidity (G)	11.3 x 10 ³ ksi	77.6 Gpa
Coefficient of Expansion	8.1 microinches/in.-°F (70-1000°F)	14.5 μm/m-°C (20-538°C)
Electrical Resistivity	46.6 μ ohm.in	118.36 μ ohm.cm
Thermal Conductivity	63 Btu-in./ft. ² hr.-°F	9.1 W/m-K

Applicable Specifications

Strip and Foil AMS 5536

Typical Mechanical Properties

Condition	Heat Treatment	Tensile Strength	Suggested Operating Conditions
Annealed	2125°F (1163°C)	105 ksi (MPa) min	-300°F to 2200°F (-184°C to 1205°C)

Hastelloy® is a registered trademark of Haynes International, Inc.

Phone: 1.888.843.2350

Elgiloy Specialty Metals - Strip
Products

1565 Fleetwood Dr.
Elgin, IL 60123 USA

WWW.ELGILOY.COM

LIMITATION OF LIABILITY AND DISCLAIMER OF WARRANTY:

The content in these data sheets is provided primarily by third-party melting mills and is provided for reference only. It is not intended for engineering or design.

Applications may be discussed, however, Elgiloy Specialty Metals does not recommend or endorse any material for any particular end use or application.

The data included in this data sheet are typical values and may vary.

Elgiloy Specialty Metals makes no representations or warranties, express or implied, as to the accuracy, completeness, condition, suitability, performance, fitness for a particular purpose, or merchantability of any information contained in any data sheet.

In no event will Elgiloy Specialty Metals be liable for any damages whatsoever arising from the use of the information included in the data sheets.