



Specialty Metals – Strip Products

Haynes® 242® Alloy

UNS N10242
W. Nr N/A

Haynes® 242® alloy is an age hardenable nickel-chromium-molybdenum alloy that combines high temperature strength, low thermal expansion, and good oxidation resistance. It derives its strength from a long range ordering reaction upon aging.

Industries served: aerospace, nuclear fuel processing, chemical processing.

Applications include: seal rings, containment rings, rocket nozzles, pumps, high temperature fluoride bearing environments.

Nominal Composition

	C	Mn	Si	P	S	Cr	Co	Mo	Al	Fe	Cu	B	Ni
min	-	-	-	-	-	7.00	-	24.00	-	-	-	-	
max	0.03	0.80	0.80	0.030	0.015	9.00	1.00	26.00	0.50	2.00	0.50	0.00	BAL

Physical Properties

	At 70°F	At 20°C
Density	0.327 lb/in ³	9.05 g/cm ³
Modulus of Elasticity (E)	33.2 x 10 ³ ksi	229 GPa
Coefficient of Expansion	6.8 microinches/in.-°F (70-1000°F)	12.2 μm/m-°C (20-538°C)
Electrical Resistivity	48.0 μ ohm.in	122.0 μ ohm.cm
Thermal Conductivity	75.7 Btu-in./ft. ² hr.-°F	11.3 W/m-K

Applicable Specifications

Strip	ASTM B434
-------	-----------

Typical Mechanical Properties – Spring Applications

Condition	Heat Treatment	Tensile Strength	Suggested Operating Conditions
Annealed	1900-2050°F (925-1120°C)	105 ksi (725MPa) min	-300°F to 1800°F (-184°C to 982°C)
Annealed and Aged	1200°F, 24h	187 ksi (1288 MPA) typ	-300°F to 1800°F (-184°C to 982°C)

Haynes® and Haynes 242® are registered trademarks of Haynes International, Inc.

Phone: 1.888.843.2350

Elgiloy Specialty Metals - Strip
Products

1565 Fleetwood Dr.
Elgin, IL 60123 USA

WWW.ELGILOY.COM

LIMITATION OF LIABILITY AND DISCLAIMER OF WARRANTY:

The content in these data sheets is provided primarily by third-party melting mills and is provided for reference only. It is not intended for engineering or design.

Applications may be discussed, however, Elgiloy Specialty Metals does not recommend or endorse any material for any particular end use or application.

The data included in this data sheet are typical values and may vary.

Elgiloy Specialty Metals makes no representations or warranties, express or implied, as to the accuracy, completeness, condition, suitability, performance, fitness for a particular purpose, or merchantability of any information contained in any data sheet.

In no event will Elgiloy Specialty Metals be liable for any damages whatsoever arising from the use of the information included in the data sheets.