



Specialty Metals – Strip Products

L-605 / Haynes 25[®]

**UNS R30605
W.Nr 2.4964 / 2.4967**

Haynes[®] 25/L605 is a nonmagnetic, Cobalt-Nickel-Chromium-Tungsten alloy that combines excellent high temperature strength with good resistance to oxidization and carburization in environments up to 980°C (1795°F) for long exposures. It also has excellent resistance to sulphidation. Haynes[®] 25/L605 responds very well to cold working. Applications include: Combustor liners, furnace liners, gas turbine rotors, nozzle diaphragm valves, springs, heart valves Industries supplied include: Aerospace, Land-Based Turbines, Power Generation, Electronics, and Medical.

Nominal Composition

	C	Mn	Si	P	S	Cr	Ni	W	Fe	Co			
min	0.05	1.00				19.00	9.00	14.00					
max	0.15	2.00	0.40	0.040	0.030	21.00	11.00	16.00	3.00	Balance			

Physical Properties

	At 70°F	At 20°C
Density	0.33 lb/in ³	9.1 g/cm ³
Modulus of Elasticity (E)	32.6 x 10 ³ ksi	225 GPa
Modulus of Rigidity (G)	14.2 x 10 ³ ksi	98 GPa
Coefficient of Expansion	6.8 microinches/in.-°F (70-600°F)	12 μm/m-°C (20-538°C)
Electrical Resistivity	34.9 μ ohm.in	89 μ ohm.cm
Thermal Conductivity	65 Btu-in./ft. ² hr.-°F	9.4 W/m-K

Applicable Specifications

Strip and Foil	AMS 5537, Rolls Royce MSRR 7053, NACE MR0175/ISO 15156
----------------	--

Typical Mechanical Properties

Condition	Heat Treatment	Tensile Strength	Suggested Operating Conditions
Annealed		130 ksi (896 MPa) Min.	

Haynes[®] is a registered trademark of Haynes International, Inc.

Phone: 1.888.843.2350

Elgiloy Specialty Metals - Strip Products

1565 Fleetwood Dr.
Elgin, IL 60123 USA

WWW.ELGILOY.COM

LIMITATION OF LIABILITY AND DISCLAIMER OF WARRANTY:

The content in these data sheets is provided primarily by third-party melting mills and is provided for reference only. It is not intended for engineering or design.

Applications may be discussed, however, Elgiloy Specialty Metals does not recommend or endorse any material for any particular end use or application.

The data included in this data sheet are typical values and may vary.

Elgiloy Specialty Metals makes no representations or warranties, express or implied, as to the accuracy, completeness, condition, suitability, performance, fitness for a particular purpose, or merchantability of any information contained in any data sheet.

In no event will Elgiloy Specialty Metals be liable for any damages whatsoever arising from the use of the information included in the data sheets.