



Specialty Metals – Strip Products

Haynes® HR-120®

**UNS N08120
W. Nr N/A**

Haynes® HR-120® alloy is a solid solution strengthened heat resistant alloy that provides excellent strength at elevated temperature combined with very good resistance to carburizing and sulfidizing environments. Its oxidation resistance is comparable to other widely used Fe-Ni-Cr materials but its strength at temperatures up to 2200°F is significantly higher. The alloy can be readily cold or hot formed and is commonly welded using Haynes 556® filler wire. Applications include: Heat treat furnaces and fixtures, incinerators, radiant tubes, recuperators, fluidized bed components.

Nominal Composition

	C	Mn	Si	P	S	Cr	Co	Mo	Al	Fe	Cu	W	Ni
min	0.02	-	-	-	-	23.00	-	-	-	-	-	-	35.00
max	0.10	1.50	1.00	0.040	0.030	27.00	3.00	2.50	0.40	Bal	0.50	2.50	39.00

Physical Properties

	At 70°F	At 20°C
Density	0.291 lb/in ³	8.07 g/cm ³
Modulus of Elasticity (E)	28.6 x 10 ³ ksi	197 GPa
Coefficient of Expansion	9.0 microinches/in.-°F (70-1000°F)	16.1 μm/m-°C (20-538°C)
Electrical Resistivity	41.1 μ ohm.in	105.2 μ ohm.cm
Thermal Conductivity	78 Btu-in./ft. ² hr.-°F	11.4 W/m-K

Applicable Specifications

Strip	ASTM B409
-------	-----------

Typical Mechanical Properties – Spring Applications

Condition	Heat Treatment	Tensile Strength	Suggested Operating Conditions
Annealed	2150-2210°F (1177-1210°C)	90 ksi (621MPa) min	-300°F to 2200°F (-184°C to 1200°C)

Haynes® and Haynes HR-120® are registered trademarks of Haynes International, Inc.

Phone: 1.888.843.2350

Elgiloy Specialty Metals - Strip
Products
1565 Fleetwood Dr.
Elgin, IL 60123 USA

WWW.ELGILOY.COM

LIMITATION OF LIABILITY AND DISCLAIMER OF WARRANTY:

The content in these data sheets is provided primarily by third-party melting mills and is provided for reference only. It is not intended for engineering or design.

Applications may be discussed, however, Elgiloy Specialty Metals does not recommend or endorse any material for any particular end use or application.

The data included in this data sheet are typical values and may vary.

Elgiloy Specialty Metals makes no representations or warranties, express or implied, as to the accuracy, completeness, condition, suitability, performance, fitness for a particular purpose, or merchantability of any information contained in any data sheet.

In no event will Elgiloy Specialty Metals be liable for any damages whatsoever arising from the use of the information included in the data sheets.