



Specialty Metals – Strip Products

Incoloy® Alloy 800

UNS N08800
W.Nr 1.4876

Incoloy® Alloy 800 is used for its corrosion resistance, heat resistance, strength, and stability at high temperatures. It offers general corrosion resistance to many aqueous media and resists stress corrosion cracking. At elevated temperatures it resists oxidation, carburization, and sulfidation along with maintaining good rupture and creep strength. Applications include furnace components and equipment, petrochemical furnace cracker tubes, pigtailed headers, sheathes for electrical heating elements, steam generator tubing, and domestic appliances. Industries supplied include: Chemical, thermal, and food processing, and nuclear.

Nominal Composition

	C	Mn	Si	P	S	Cr	Ni	Ti	Al	Cu	Fe		
min	-	-	-	-	-	19.00	30.00	0.15	0.15	-	-		
max	0.10	1.50	1.00	0.035	0.015	23.00	35.00	0.60	0.60	0.75	Bal		

Physical Properties

	At 70°F	At 20°C
Density	0.287 lb/in ³	7.94 g/cm ³
Modulus of Elasticity (E)	28.50 x 10 ³ ksi	197 GPa
Modulus of Rigidity (G)	11 x 10 ³ ksi	76 GPa
Coefficient of Expansion	9.4 microinches/in.-°F (70-1000°F)	16.8 μm/m-°C (20-538°C)
Electrical Resistivity	38.9 μ ohm.in	98.9 μ ohm.cm
Thermal Conductivity	80 Btu-in./ft. ² hr.-°F	11.5 W/m-K

Applicable Specifications

Strip	AMS 5871, ASTM A240, ASTM B409
-------	--------------------------------

Typical Mechanical Properties – Spring Applications

Condition	Heat Treatment	Tensile Strength	Suggested Operating Conditions
Annealed	1900°F (1036°C)	75 ksi (520 MPa) min	-300°F to 1500°F (-184°C to 816°C)

INCOLOY® is a registered trademark of the Special Metals Corporation group of companies.

Phone: 1.888.843.2350

Elgiloy Specialty Metals - Strip Products
1565 Fleetwood Dr.
Elgin, IL 60123 USA

WWW.ELGILOY.COM

LIMITATION OF LIABILITY AND DISCLAIMER OF WARRANTY:

The content in these data sheets is provided primarily by third-party melting mills and is provided for reference only. It is not intended for engineering or design.

Applications may be discussed, however, Elgiloy Specialty Metals does not recommend or endorse any material for any particular end use or application.

The data included in this data sheet are typical values and may vary.

Elgiloy Specialty Metals makes no representations or warranties, express or implied, as to the accuracy, completeness, condition, suitability, performance, fitness for a particular purpose, or merchantability of any information contained in any data sheet.

In no event will Elgiloy Specialty Metals be liable for any damages whatsoever arising from the use of the information included in the data sheets.