



Specialty Metals – Strip Products

Incoloy® Alloy 825

UNS N08825
W.Nr 2.4858

Incoloy® Alloy 825 is a Nickel-Iron-Chrome alloy with excellent resistance to sulfuric and phosphoric acids. It is also resistant to oxidizing and reducing acids, stress corrosion cracking, pitting, and intergranular corrosion. Applications include chemical processing, pollution control, oil and gas recovery, acid production, pickling operations, nuclear fuel reprocessing, and radioactive waste handling. Industries supplied include: Chemical and petrochemical, oil & gas, pollution control, and nuclear.

Nominal Composition

	C	Mn	Si	P	S	Cr	Ni	Ti	Al	Cu	Fe	Mo
min	-	-	-	-	-	19.50	38.00	0.60	-	1.50	22.00	2.50
max	0.05	1.00	0.50	-	0.030	23.50	46.00	1.20	0.20	3.00	-	3.50

Physical Properties

	At 70°F	At 20°C
Density	0.294 lb/in ³	8.14 g/cm ³
Modulus of Elasticity (E)	28.30 x 10 ³ ksi	196 GPa
Modulus of Rigidity (G)	11 x 10 ³ ksi	76 GPa
Coefficient of Expansion	8.8 microinches/in.-°F (70-1000°F)	15.8 μm/m-°C (20-538°C)
Electrical Resistivity	44.4 μ ohm.in	113.0 μ ohm.cm
Thermal Conductivity	76.8 Btu-in./ft. ² hr.-°F	11.1 W/m-K

Applicable Specifications

Strip	ASTM B424, NACE MR0175
-------	------------------------

Typical Mechanical Properties – Spring Applications

Condition	Heat Treatment	Tensile Strength	Suggested Operating Conditions
Annealed	1832°F (1000°C)	85 ksi (586 MPa) min	-300°F to 1600°F (-184°C to 871°C)

INCOLOY® is a registered trademark of the Special Metals Corporation group of companies.

Phone: 1.888.843.2350

Elgiloy Specialty Metals - Strip Products
1565 Fleetwood Dr.
Elgin, IL 60123 USA

WWW.ELGILOY.COM

LIMITATION OF LIABILITY AND DISCLAIMER OF WARRANTY:

The content in these data sheets is provided primarily by third-party melting mills and is provided for reference only. It is not intended for engineering or design.

Applications may be discussed, however, Elgiloy Specialty Metals does not recommend or endorse any material for any particular end use or application.

The data included in this data sheet are typical values and may vary.

Elgiloy Specialty Metals makes no representations or warranties, express or implied, as to the accuracy, completeness, condition, suitability, performance, fitness for a particular purpose, or merchantability of any information contained in any data sheet.

In no event will Elgiloy Specialty Metals be liable for any damages whatsoever arising from the use of the information included in the data sheets.