



Specialty Metals – Strip Products

Inconel® alloy 600

UNS N06600
W.Nr 2.4816

Inconel® 600 is a Nickel-Chromium-Iron alloy with good corrosion resistance, oxidation resistance, and high strength at high temperatures. Inconel® 600 is highly resistant to chloride-ion stress-corrosion cracking due to the high nickel content. Age-hardening treatments are not required, as Inconel 600® is hardened and strengthened through cold work only. Inconel® 600 can operate from cryogenic temperatures to 700°F. Applications include reactor vessels, furnace seals fans and fixtures and process equipment. Industries supplied include: Chemical Processing, Heat Treating, Nuclear, and Aerospace.

Nominal Composition

	C	Mn	Si	P	S	Cr	Ni	Fe	Co	Nb	Ti	Al	Cu
min						14.00	72.00	6.00					
max	0.15	1.00	0.50	0.040	0.015	17.00		10.00	1.00	1.00	0.50	0.35	0.50

Physical Properties

	At 70°F	At 20°C
Density	0.306 lb/in ³	8.47 g/cm ³
Modulus of Elasticity (E)	31.1 x 10 ³ ksi	214 GPa
Modulus of Rigidity (G)	11.7 x 10 ³ ksi	81.0 GPa
Coefficient of Expansion	7.9 microinches/in.-°F (70-600°F)	14.2 μm/m-°C (20-538°C)
Electrical Resistivity	40.6 μ ohm.in	103 μ ohm.cm
Thermal Conductivity	103 Btu-in./ft. ² hr.-°F	14.9 W/m-K

Applicable Specifications

Strip and Foil	ASTM B168, AMS 5540
----------------	---------------------

Typical Mechanical Properties

Condition	Heat Treatment	Tensile Strength	Suggested Operating Conditions
Annealed	1975°F (1079°C)	80 - 110 ksi (552-758 MPa)	-300°F to 700°F (-184°C to 370°C)
Spring Temper		125 - 185 ksi (862-1275 MPa)	-300°F to 700°F (-184°C to 370°C)

INCONEL® is a registered trademark of the Special Metals Corporation group of companies.

Phone: 1.888.843.2350

Elgiloy Specialty Metals - Strip
Products

1565 Fleetwood Dr.
Elgin, IL 60123 USA

WWW.ELGILOY.COM

LIMITATION OF LIABILITY AND DISCLAIMER OF WARRANTY:

The content in these data sheets is provided primarily by third-party melting mills and is provided for reference only. It is not intended for engineering or design.

Applications may be discussed, however, Elgiloy Specialty Metals does not recommend or endorse any material for any particular end use or application.

The data included in this data sheet are typical values and may vary.

Elgiloy Specialty Metals makes no representations or warranties, express or implied, as to the accuracy, completeness, condition, suitability, performance, fitness for a particular purpose, or merchantability of any information contained in any data sheet.

In no event will Elgiloy Specialty Metals be liable for any damages whatsoever arising from the use of the information included in the data sheets.