

Inconel® alloy 601

UNS N06601
W.Nr 2.4851

Inconel® 601 is a general purpose Nickel-Chromium-Iron alloy for applications requiring good resistance to heat and corrosion. The most important property is its outstanding resistance to high temperature oxidation even under cyclical heating and cooling. Inconel® 601 also has good resistance to aqueous corrosion, has high mechanical strength, and is readily formed, machined, and welded. Age-hardening treatments are not required, as Inconel 601® is hardened and strengthened through cold work only.

Applications include petrochemical processing, industrial furnace components, gas turbine components.

Industries supplied include: Chemical Processing, Thermal Processing, Aerospace, Pollution Control, and Power Generation.

Nominal Composition

	C	Mn	Si	P	S	Cr	Ni	Fe	Co	Nb	Ti	Al	B
min	-	-	-	-	-	21.00	58.00	-	-	-	0.10	1.00	-
max	0.10	1.00	0.50	-	0.015	25.00	63.00	Bal	-	-	0.60	1.70	0.006

Physical Properties

	At 70°F	At 20°C
Density	0.293 lb/in ³	8.11 g/cm ³
Modulus of Elasticity (E)	30.0 x 10 ³ ksi	207 GPa
Modulus of Rigidity (G)	11.8 x 10 ³ ksi	81.2 GPa
Coefficient of Expansion	8.1 microinches/in.-°F (70-600°F)	15.2 μm/m-°C (20-538°C)
Electrical Resistivity	46.5 μ ohm.in	118 μ ohm.cm
Thermal Conductivity	78 Btu-in./ft. ² hr.-°F	11.2 W/m-K

Applicable Specifications

Strip	ASTM B168, AMS 5870, Din 17750
-------	--------------------------------

Typical Mechanical Properties – Spring Applications

Condition	Heat Treatment	Tensile Strength	Suggested Operating Conditions
Annealed	1975°F (1079°C)	80 ksi (552 MPa) min 95 ksi (552 MPa) typ	-300°F to 1830°F (-184°C to 1000°C)

INCONEL® is a registered trademark of the Special Metals Corporation group of companies.

Phone: 1.888.843.2350

Elgiloy Specialty Metals - Strip
Products

1565 Fleetwood Dr.
Elgin, IL 60123 USA

WWW.ELGILOY.COM

LIMITATION OF LIABILITY AND DISCLAIMER OF WARRANTY:

The content in these data sheets is provided primarily by third-party melting mills and is provided for reference only. It is not intended for engineering or design.

Applications may be discussed, however, Elgiloy Specialty Metals does not recommend or endorse any material for any particular end use or application.

The data included in this data sheet are typical values and may vary.

Elgiloy Specialty Metals makes no representations or warranties, express or implied, as to the accuracy, completeness, condition, suitability, performance, fitness for a particular purpose, or merchantability of any information contained in any data sheet.

In no event will Elgiloy Specialty Metals be liable for any damages whatsoever arising from the use of the information included in the data sheets.