

Inconel® alloy X750

UNS N07750
W.Nr 2.4669

Inconel® X750 is a precipitation hardenable Nickel-Chromium alloy with high strength at temperatures up to 1300°F (704°C) and oxidation resistance up to 1800°F (982°C). Inconel® X750 offers excellent resistance to relaxation and as a result it is widely used for springs operating at elevated temperatures.

Applications include: springs operating from cryogenic temperatures up to 1300°F (704°C), fasteners and components requiring resistance to high temperature and corrosive environments.

Industries supplied include: Oil & Gas Extraction and Processing, Nuclear, Aerospace, Power Generation and Automotive

Nominal Composition

	C	Mn	Si	S	Cr	Nb	Ti	Al	Fe	Co	Ta	Cu	Ni + Co
min					14.00	0.70	2.25	0.40	5.00				70.00
max	0.08	0.35	0.35	0.010	17.00	1.20	2.75	1.00	9.00	1.00	0.05	0.50	

Physical Properties

	At 70°F	At 20°C
Density	0.299 lb/in ³	8.28 g/cm ³
Modulus of Elasticity (E)	31.0 x 10 ³ ksi	214 GPa
Modulus of Rigidity (G)	12.0 x 10 ³ ksi	82.7 GPa
Coefficient of Expansion	7.8 microinches/in.-°F (70-600°F)	14.5 µm/m-°C (20-538°C)
Electrical Resistivity	48.0 µ ohm.in	122 µ ohm.cm
Thermal Conductivity	83 Btu-in./ft. ² hr.-°F	12.0 W/m-K

Applicable Specifications

Strip and Foil	AMS 5542, AMS 5598
----------------	--------------------

Typical Mechanical Properties

Condition	Heat Treatment	Tensile Strength	Suggested Operating Conditions
Annealed		130 ksi max (896 MPa) max	
Spring Temper		160 – 220 ksi (1100 – 1517 MPa)	
After Precipitation Heat Treat	per AMS 5542 / AMS 5598	160 ksi (1100 MPa) Min	Dependant on heat treat. See SMC publication for details.

INCONEL® is a registered trademark of the Special Metals Corporation group of companies.

Elgiloy Specialty Metals - Strip
Products

Phone: 1.888.843.2350

1565 Fleetwood Dr.
Elgin, IL 60123 USA

WWW.ELGILOY.COM

LIMITATION OF LIABILITY AND DISCLAIMER OF WARRANTY:

The content in these data sheets is provided primarily by third-party melting mills and is provided for reference only. It is not intended for engineering or design.

Applications may be discussed, however, Elgiloy Specialty Metals does not recommend or endorse any material for any particular end use or application.

The data included in this data sheet are typical values and may vary.

Elgiloy Specialty Metals makes no representations or warranties, express or implied, as to the accuracy, completeness, condition, suitability, performance, fitness for a particular purpose, or merchantability of any information contained in any data sheet.

In no event will Elgiloy Specialty Metals be liable for any damages whatsoever arising from the use of the information included in the data sheets.