

Nickel 200/201 alloys

UNS N02200 & N02201
W. Nr 2.4060/2.4066 & 2.4061/2.4068

Applicable Specifications

Strip and Foil | AMS 5553, ASTM B162, DIN 17740, DIN 17750

Description: Nickel 200 is a solid solution strengthened, commercially pure material with good mechanical properties over a wide range of temperatures. It has excellent resistance to many corrosives, particularly hydroxides. Nickel 200 has high electrical and thermal conductivity and is ferromagnetic. It offers very good weldability and formability.

Applications include: Burst disks, evaporators, combustion boats, electronic components, chemical drums, reactors, vessels, missile components

Industries supplied include: Chemical processing and manufacturing, Electronics, Aerospace & Defense

Nominal Composition

	C	Mn	Si	S	Ni	Cu	Fe
min	-	-	-	-	Bal	-	-
max	0.15/0.02	0.35	0.35	0.01		0.25	0.40

Physical Properties

	At 70°F	At 20°C
Density	0.321 lb/in ³	8.9 g/cm ³
Modulus of Elasticity (E)	29.7 x 10 ³ ksi	205 GPa
Modulus of Rigidity (G)	11.55 x 10 ³ ksi	79.6 GPa
Coefficient of Expansion	8.44 microinches/in.-°F (70-932°F)	15.2 μm/m-°C (20-500°C)
Electrical Resistivity	3.15 μ ohm.in	8.5 μ ohm.cm
Thermal Conductivity	487 Btu-in./ft. ² hr.-°F	70.2 W/m-K

Typical Mechanical Properties

Condition	Heat Treatment	Tensile Strength	Suggested Operating Conditions
Annealed	1300-1700 °F (705-925 °C)	55-75 ksi (380-520 MPa)	-300°F to 1000°F (-184°C to 540°C)
Spring Temper	(Stress relieve as needed)	90 ksi min	-300°F to 1000°F (-184°C to 540°C)

Elgiloy Specialty Metals - Strip Products

1565 Fleetwood Dr.
Elgin, IL 60123 USA

Phone: 1-888-843-2350

www.elgiloy.com

LIMITATION OF LIABILITY AND DISCLAIMER OF WARRANTY:

The content in these data sheets is provided primarily by third-party melting mills and is provided for reference only. It is not intended for engineering or design.

Applications may be discussed, however, Elgiloy Specialty Metals does not recommend or endorse any material for any particular end use or application.

The data included in this data sheet are typical values and may vary.

Elgiloy Specialty Metals makes no representations or warranties, express or implied, as to the accuracy, completeness, condition, suitability, performance, fitness for a particular purpose, or merchantability of any information contained in any data sheet.

In no event will Elgiloy Specialty Metals be liable for any damages whatsoever arising from the use of the information included in the data sheets.