

Elgiloy®

**UNS R30003
W.Nr 2.4711**

Elgiloy® is a non-magnetic Cobalt-Chromium-Nickel-Molybdenum alloy having a unique combination of very high strength, excellent corrosion resistance and high fatigue strength. Elgiloy® is highly resistant to sulfide stress corrosion cracking and as a result is the alloy of choice in the most demanding sour well environments. In seawater Elgiloy® is virtually immune to crevice and stress corrosion and pitting even at the highest strength levels and can operate at cryogenic temperatures up to 850°F (454°C).

Applications include springs, torsion bars, seals, medical devices & implants and orthodontic wire.

Industries supplied include: Oil & Gas Extraction, Medical & Dental, Aerospace, Defense and Space Exploration.

Nominal Composition

	Co	Cr	Ni	Mo	Mn	Fe	Si	C	Be	P	S
min	39	19	14	6	1.5						
max	41	21	16	8	2.5	balance	1.2	0.15	0.1	0.015	0.015

Physical Properties

	At 70°F	At 20°C
Density	0.300 lb/in ³	8.30 g/cm ³
Modulus of Elasticity (E)	Up to 32.0 x 10 ³ ksi	190 GPa
Modulus of Rigidity (G)	11.2 x 10 ³ ksi	77.2 GPa
Coefficient of Expansion	8.4 microinches/in.-°F (70-600°F)	15.2 x μm/m-°C (20-300°C)
Electrical Resistivity	39.2 μ ohm.in	99.6 μ ohm.cm
Thermal Conductivity	86.5 Btu-in./ft. ² hr.-°F	12.5 W/m-K

Applicable Specifications

Wire & Bar | AMS 5833, AMS 5834, ASTM F1058, NACE MR0175 (ISO 15156-3), ISO 5832-7.

Typical Mechanical Properties – Spring Applications

Condition	Heat Treatment	Tensile Strength	Suggested Operating Conditions
Annealed	2048°F (1120°C)	120 – 150 ksi (830-1035 MPa)	-300°F to 850°F (-184°C to 454°C)
Spring Temper		220 – 290 ksi (1515-2000 MPa)	-300°F to 850°F (-184°C to 454°C)
Spring Temper + Aged	After spring coiling. Age: 980°F (527°C) for 5 hours.	260 – 330 ksi (1790-2275 MPa)	-300°F to 850°F (-184°C to 454°C)

Elgiloy® is a registered trademark of Elgiloy Specialty Metals.

Elgiloy Specialty Metals - Wire Products
356 N.Cross Street
Sycamore, IL 60178 USA

Phone: 1 847 695 1900
WWW.ELGILOY.COM

REV 2024 04 02

LIMITATION OF LIABILITY AND DISCLAIMER OF WARRANTY:

The content in these data sheets is provided primarily by third-party melting mills and is provided for reference only. It is not intended for engineering or design.

Applications may be discussed, however, Elgiloy Specialty Metals does not recommend or endorse any material for any particular end use or application.

The data included in this data sheet are typical values and may vary.

Elgiloy Specialty Metals makes no representations or warranties, express or implied, as to the accuracy, completeness, condition, suitability, performance, fitness for a particular purpose, or merchantability of any information contained in any data sheet.

In no event will Elgiloy Specialty Metals be liable for any damages whatsoever arising from the use of the information included in the data sheets.