

## Hastelloy® alloy C-276

**UNS N10276**  
**W.Nr 2.4819**

Hastelloy® alloy C-276 is a Nickel-Molybdenum-Chromium corrosion resistant alloy. The alloy is resistant to pitting, crevice corrosion, and stress corrosion cracking. Hastelloy® C-276 is hardened only by cold-working. Hastelloy® C-276 can operate from cryogenic temperatures up to 750°F (400°C).

Applications include springs, heat exchangers, and seals.

Industries supplied include: Chemical Processing, Pollution Control, Pulp and Paper Production, and Waste Treatment.

### Nominal Composition

	Mo	Cr	Fe	W	Co	Mn	Ni	V	Si	P	S	C
min	15	14.5	4	3								
max	17	16.5	7	4.5	2.5	1	balance	0.35	0.08	0.04	0.03	0.01

### Physical Properties

	At 70°F	At 20°C
<b>Density</b>	0.321 lb/in <sup>3</sup>	8.89 g/cm <sup>3</sup>
<b>Modulus of Elasticity (E)</b>	29.8 x 10 <sup>3</sup> ksi	205 GPa
<b>Modulus of Rigidity (G)</b>	11.4 x 10 <sup>3</sup> ksi	79 GPa
<b>Coefficient of Expansion</b>	7.1 microinches/in.-°F (70-600°F)	12.8 x μm/m-°C (20-300°C)
<b>Electrical Resistivity</b>	51 μ ohm.in	130 μ ohm.cm
<b>Thermal Conductivity</b>	67.9 Btu-in./ft. <sup>2</sup> hr.-°F	9.8 W/m-K

### Applicable Specifications

Wire & Bar | ASTM B574, AWS A5.14, NACE MRO175 (ISO 15156-3).

### Typical Mechanical Properties – Spring Applications

Condition	Heat Treatment	Tensile Strength	Suggested Operating Conditions
<b>Annealed</b>	2048°F (1120°C)	120 – 160 Ksi (830 – 1100 MPa)	-300°F to 750°F (-184°C to 400°C)
<b>Spring Temper</b>		200 – 240 ksi (1380 – 1655 MPa)	-300°F to 750°F (-184°C to 400°C)

Hastelloy® is a registered trademark of Haynes International, Inc.

Elgiloy Specialty Metals - Wire Products  
356 N. Cross Street  
Sycamore, IL 60178 USA

**Phone: 1 847 695 1900**  
[WWW.ELGILOY.COM](http://WWW.ELGILOY.COM)

REV 2024 04 02

## **LIMITATION OF LIABILITY AND DISCLAIMER OF WARRANTY:**

The content in these data sheets is provided primarily by third-party melting mills and is provided for reference only. It is not intended for engineering or design.

Applications may be discussed, however, Elgiloy Specialty Metals does not recommend or endorse any material for any particular end use or application.

The data included in this data sheet are typical values and may vary.

Elgiloy Specialty Metals makes no representations or warranties, express or implied, as to the accuracy, completeness, condition, suitability, performance, fitness for a particular purpose, or merchantability of any information contained in any data sheet.

In no event will Elgiloy Specialty Metals be liable for any damages whatsoever arising from the use of the information included in the data sheets.