

Hastelloy® alloy C-2000

UNS N06200
W.Nr 2.4675

Hastelloy® alloy C-2000 is a versatile Nickel-Chromium-Molybdenum alloy with excellent corrosion resistance to all acids over a large temperature range. It is highly resistant to a wide range of oxidizing and non-oxidizing chemicals and exhibits outstanding resistance to pitting and crevice attack in the presence of chlorides and other halides.

Applications include springs, fasteners, pump and mixer shafts.

Industries supplied include: Chemical Processing.

Nominal Composition

	Cr	Mo	Fe	Co	Cu	Ni	C	Mn	Al	Si	P
min	22	15			1.3						
max	24	17	3	2	1.9	balance	0.01	0.5	0.5	0.08	0.025

Physical Properties

	At 70°F	At 20°C
Density	.307 lb/in ³	8.5 g/cm ³
Modulus of Elasticity (E)	30 x 10 ³ ksi	207 GPa
Modulus of Rigidity (G)	11.5 x 10 ³ ksi	79 GPa
Coefficient of Expansion	7 microinches/in.-°F (70-600°F)	12.6 μm/m-°C (20-300°C)
Electrical Resistivity	50.6 μ ohm.in	128 μ ohm.cm
Thermal Conductivity	63 Btu-in./ft. ² hr.-°F	9.1 W/m-K

Applicable Specifications

Wire & Bar | ASTM B574, NACE MR0175 (ISO 15156-3).

Typical Mechanical Properties – Spring Applications

Condition	Heat Treatment	Tensile Strength	Suggested Operating Conditions
Annealed	2075°F (1135°C)	100 – 140 ksi (690 – 965 MPa)	-330°F to 750°F (-200°C to 400°C)
Spring Temper		200 – 250 ksi (1380 – 1720 MPa)	-330°F to 750°F (-200°C to 400°C)

Hastelloy® is a registered trademark of Haynes International, Inc.

Phone: 1 847 695 1900

Elgiloy Specialty Metals - Wire Products
356 N.Cross Street
Sycamore, IL 60178 USA

WWW.ELGILOY.COM

LIMITATION OF LIABILITY AND DISCLAIMER OF WARRANTY:

The content in these data sheets is provided primarily by third-party melting mills and is provided for reference only. It is not intended for engineering or design.

Applications may be discussed, however, Elgiloy Specialty Metals does not recommend or endorse any material for any particular end use or application.

The data included in this data sheet are typical values and may vary.

Elgiloy Specialty Metals makes no representations or warranties, express or implied, as to the accuracy, completeness, condition, suitability, performance, fitness for a particular purpose, or merchantability of any information contained in any data sheet.

In no event will Elgiloy Specialty Metals be liable for any damages whatsoever arising from the use of the information included in the data sheets.