

Hastelloy® alloy C-22

UNS N06022
W.Nr 2.4602

Hastelloy® alloy C-22 is a Nickel-Chromium-Molybdenum alloy with excellent corrosion resistance to a wide variety of environments. It is also resistant to oxidation, pitting, crevice corrosion, intergranular attack, and stress corrosion cracking. Applications include springs, fasteners, seals, medical devices, and components used in flue gas equipment. Industries supplied include: Chemical Processing, Oil & Gas Extraction, and Power Generation.

Nominal Composition

	Cr	Mo	Fe	W	Co	Ni	V	C	Mn	S	Si
min	20	12.5	2	2.5							
max	22.5	14.5	6	3.5	2.5	balance	0.35	0.015	0.50	0.02	0.08

Physical Properties

	At 70°F	At 20°C
Density	0.311 lb/in ³	8.61 g/cm ³
Modulus of Elasticity (E)	29.9 x 10 ³ ksi	206 GPa
Modulus of Rigidity (G)	11.4 X 10 ³ ksi	79 GPa
Coefficient of Expansion	7 microinches/in.-°F (70-600°F)	12.6 μm/m-°C (20-300°C)
Electrical Resistivity	44.8 μ ohm.in	114 μ ohm.cm
Thermal Conductivity	91 Btu-in./ft. ² hr.-°F	13.2 W/m-K

Applicable Specifications

Wire & Bar | ASTM B574, AWS A5.14, NACE MR0175 (ISO 15156-3).

Typical Mechanical Properties – Spring Applications

Condition	Heat Treatment	Tensile Strength	Suggested Operating Conditions
Annealed	2048°F (1120°C)	110 – 150 ksi (758 – 1034 MPa)	-330°F to 750°F (-200°C to 400°C)
Spring Temper		200 – 240 ksi (1379 – 1655 MPa)	-330°F to 750°F (-200°C to 400°C)

Hastelloy® is a registered trademark of Haynes International, Inc.

Phone: 1 847 695 1900

Elgiloy Specialty Metals - Wire Products
356 N.Cross Street
Sycamore, IL 60178 USA

WWW.ELGILOY.COM

LIMITATION OF LIABILITY AND DISCLAIMER OF WARRANTY:

The content in these data sheets is provided primarily by third-party melting mills and is provided for reference only. It is not intended for engineering or design.

Applications may be discussed, however, Elgiloy Specialty Metals does not recommend or endorse any material for any particular end use or application.

The data included in this data sheet are typical values and may vary.

Elgiloy Specialty Metals makes no representations or warranties, express or implied, as to the accuracy, completeness, condition, suitability, performance, fitness for a particular purpose, or merchantability of any information contained in any data sheet.

In no event will Elgiloy Specialty Metals be liable for any damages whatsoever arising from the use of the information included in the data sheets.