

Haynes® 242® alloy

UNS N10242

Applicable Specifications

Wire & Bar | ASTM B434 (chemistry only)

Description: HAYNES® 242® alloy is an age-hardenable nickel-molybdenum chromium alloy which can be strengthened through an ordering reaction upon aging, while maintaining high ductility. The alloy's tensile and creep strength properties up to 1300°F (705°C) are considerably improved compared to solid solution strengthened alloys. The coefficient of thermal expansion for 242® alloy are also lower than most other alloys, and it has very good oxidation resistance up to 1500°F (815°C). Other notable characteristics include excellent low cycle fatigue properties and resistance to high-temperature fluorine rich environments.

Applications include: Seal rings, Containment rings, Duct segments, Casings, Fasteners, Nozzles, Pumps, Fluoroelastomer process equipment, HF acid processing equipment, Springs

Industries supplied include: Aerospace, Industrial Heat Treating, Power Generation, Chemical Processing

Nominal Composition

	C	Mn	Si	P	S	B	Ni	Cr	Co	Mo	La	W	Al	Fe
min	0.05	0.30	0.25	-	-	-	Bal	20.00	-	1.00	0.005	13.00	-	-
max	0.15	1.00	0.75	0.030	0.015	0.015	-	24.00	5.00	3.00	0.05	15.00	0.50	3.00

Physical Properties

	At 70°F	At 20°C
Density	0.327 lb/in ³	9.05 g/cm ³
Modulus of Elasticity (E)	33.2 x 10 ³ ksi	229 GPa
Coefficient of Expansion	8.3 μin/in-°F (70-1800°F)	15.0 μm/m-°C (25-1000°C)
Electrical Resistivity	48.0 μohm-in	122.0 μohm-cm
Thermal Conductivity	75.7 Btu-in/ft ² -hr-°F	11.3 W/m-°C

Typical Mechanical Properties

Condition	Heat Treatment	Tensile Strength	Suggested Operating Conditions
Annealed	1900-2050°F (1040-1120°C)	110-140 ksi (758-965 MPa)	Up to 1500°F (815°C)
Aged	1200°F (650°C) 24-48 hours	170 ksi min (1172 MPa)	Up to 1200°F (650°C)

Haynes® 242® is a registered trademark of Haynes International, Inc.

Elgiloy Specialty Metals – Wire Products

356 North Cross Street
Sycamore, IL 60178 USA
Phone: 1-847-695-1900

www.elgiloy.com

LIMITATION OF LIABILITY AND DISCLAIMER OF WARRANTY:

The content in these data sheets is provided primarily by third-party melting mills and is provided for reference only. It is not intended for engineering or design.

Applications may be discussed, however, Elgiloy Specialty Metals does not recommend or endorse any material for any particular end use or application.

The data included in this data sheet are typical values and may vary.

Elgiloy Specialty Metals makes no representations or warranties, express or implied, as to the accuracy, completeness, condition, suitability, performance, fitness for a particular purpose, or merchantability of any information contained in any data sheet.

In no event will Elgiloy Specialty Metals be liable for any damages whatsoever arising from the use of the information included in the data sheets.