

Haynes® 263 alloy

UNS N07263

Applicable Specifications

Wire & Bar | AMS 5872 (chemistry only)

Description: Haynes® 263 alloy is an age-hardenable Ni-Co-Cr-Mo alloy designed to combine very good aged strength with excellent fabrication characteristics in the annealed condition. While its strength at high temperature is not quite as high as Waspaloy or R-41, it is far easier to form or weld than these alloys. Haynes® 263 exhibits excellent intermediate temperature tensile ductility and is not normally subject to strain age cracking problems common for gamma prime strengthened alloys. In many applications, Haynes® 282® has replaced Haynes® 263 due to its superior mechanical properties and further improved fabricability.

Applications include: Low temperature combustors, Transition liners, Rings

Industries supplied include: Aerospace, Land Based Turbines

Nominal Composition

	C	Mn	Si	P	S	Cr	Ni	Co	Mo	Ti	Al	Ti+Al	B	Cu	Fe
min	0.04	-	-	-	-	19.00	Bal	19.00	5.60	1.90	0.30	2.40	-	-	-
max	0.08	0.60	0.40	0.015	0.007	21.00		21.00	6.10	2.40	0.60	2.80	0.005	0.20	0.70

Physical Properties

	At 70°F	At 20°C
Density	0.302 lb/in ³	8.36 g/cm ³
Modulus of Elasticity (E)	32.1 x 10 ³ ksi	221 GPa
Coefficient of Expansion	9.9 µin/in-°F (70-1800°F)	18.1 µm/m-°C (25-1000°C)
Electrical Resistivity	45.3 µohm-in	115 µohm-cm
Thermal Conductivity	81 Btu-in/ft ² -hr-°F	11.7 W/m-°C

Typical Mechanical Properties

Condition	Heat Treatment	Tensile Strength	Suggested Operating Conditions
Annealed	1900-1050°F (1038-1177°C)	110-140 ksi (758-965 MPa)	Up to 1650°F (900°C)
Aged	1475°F (802°C) for 8 hours	160 ksi min (1103 MPa)	Up to 1300°F (704°C)

Haynes® 263 and Haynes® 282® are registered trademarks of Haynes International, Inc.

Elgiloy Specialty Metals – Wire Products

356 North Cross Street
 Sycamore, IL 60178 USA
 Phone: 1-847-695-1900

www.elgiloy.com

LIMITATION OF LIABILITY AND DISCLAIMER OF WARRANTY:

The content in these data sheets is provided primarily by third-party melting mills and is provided for reference only. It is not intended for engineering or design.

Applications may be discussed, however, Elgiloy Specialty Metals does not recommend or endorse any material for any particular end use or application.

The data included in this data sheet are typical values and may vary.

Elgiloy Specialty Metals makes no representations or warranties, express or implied, as to the accuracy, completeness, condition, suitability, performance, fitness for a particular purpose, or merchantability of any information contained in any data sheet.

In no event will Elgiloy Specialty Metals be liable for any damages whatsoever arising from the use of the information included in the data sheets.