

## **Elgiloy Specialty Metals – Wire Products**

10.4 W/m-°C

## Haynes® alloy 188

UNS R30188 W.Nr 2.4683

## **Applicable Specifications**

Wire & Bar

AMS 5772, GE B50A712

**Description:** Haynes® Alloy 188 is a cobalt-nickel-chromium-tungsten alloy with excellent high temperature tensile strength, sulfidation, and oxidation resistance up to 1095°C (2000°F) for long term exposures. Haynes® Alloy 188 is not age hardenable but may be cold worked to achieve higher tensile and yield strength. Haynes® Alloy 188 responds well to conventional forming and welding techniques.

**Applications include:** High Temperature and Corrosion Resistant Applications

Industries supplied include: Military and Commercial Aerospace, Chemical Processing, and Land-Based Gas Turbines

Nomina	I Compo	sition										
	С	Mn	P	S	Si	Cr	Ni	Co	В	Fe	w	La
Min	0.05				0.20	20.0	20.0	39 (bal)			13.0	0.03
Max	0.15	1.25	0.02	0.015	0.50	24.0	24.0		0.015	3.00	16.0	0.12

Physical Properties					
	At 70°F	At 20°C			
Density	0.24 lb/in <sup>3</sup>	8.98 g/cm³			
Modulus of Elasticity (E)	33.7 x 10³ ksi	232 GPa			
Modulus of Rigidity (G)	13 x 10³ ksi	90 GPa			
Coefficient of Expansion	9.1 μin/in/°F (75-1800°F)	16.5 μm/m-°C (25-1000°C)			
Electrical Resistivity	39.6 μohm-in	101.0 μohm-cm			

Typical Mechanical Properties								
Condition	Heat Treatment	Tensile Strength	Suggested Operating Conditions					
Annealed	2150°F (1177°C)	125 ksi min	-300°F to 2000°F (-185°C to 1095°C)					
Spring Temper	None	200 ksi min	-300°F to 2000°F (-185°C to 1095°C)					
Spring Temper + Aged								

72 Btu-in/ft<sup>2</sup>-hr-°F

Haynes® is a registered trademark of Haynes International, Inc.

**Thermal Conductivity** 

Elgiloy Specialty Metals – Wire Products 356 North Cross Street Sycamore, IL 60178 USA

> Phone: 1-847-695-1900 www.elgiloy.com

> > REV 2024 04 02

## LIMITATION OF LIABILITY AND DISCLAIMER OF WARRANTY:

The content in these data sheets is provided primarily by third-party melting mills and is provided for reference only. It is not intended for engineering or design.

Applications may be discussed, however, Elgiloy Specialty Metals does not recommend or endorse any material for any particular end use or application.

The data included in this data sheet are typical values and may vary.

Elgiloy Specialty Metals makes no representations or warranties, express or implied, as to the accuracy, completeness, condition, suitability, performance, fitness for a particular purpose, or merchantability of any information contained in any data sheet.

In no event will Elgiloy Specialty Metals be liable for any damages whatsoever arising from the use of the information included in the data sheets.