

Inconel® alloy 601

UNS N06601
W.Nr 2.4851

Inconel® 601 is a Nickel-Chromium-Iron corrosion and heat resistant alloy. The aluminum content gives this alloy excellent resistance to high temperature oxidation. Inconel® 601 is not age-hardenable and is only strengthened by cold working. Inconel® 601 can operate from cryogenic temperatures up to 645°F (340°C).

Applications include furnace fixtures and mesh belts.

Industries supplied include: Thermal Processing, Chemical Processing, Power Generation and Aerospace.

Nominal Composition

	Ni	Cr	Al	Cu	Mn	Fe	Si	C	S
min	58	21	1						
max	63	25	1.7	1	1	balance	0.5	0.1	0.015

Physical Properties

	At 70°F	At 20°C
Density	0.293 lb/in ³	8.11 g/cm ³
Modulus of Elasticity (E)	30 x 10 ³ ksi	207 GPa
Modulus of Rigidity (G)	11.8 x 10 ³ ksi	81.2 GPa
Coefficient of Expansion	8.1 microinches/in.-°F (70-600°F)	14.6 x μm/m-°C (20-300°C)
Electrical Resistivity	46.5 μ ohm.in	118 μ ohm.cm
Thermal Conductivity	78 Btu-in./ft. ² hr.-°F	11.2 W/m-K

Applicable Specifications

Wire & Bar | ASTM B166, AWS A5.14.

Typical Mechanical Properties – Spring Applications

Condition	Heat Treatment	Tensile Strength	Suggested Operating Conditions
Annealed	2100°F (1150°C)	90 – 115 ksi (620 – 793 MPa)	-300°F to 645°F (-184°C to 340°C)
Spring Temper		180 – 210 ksi (1240 – 1448 MPa)	-300°F to 645°F (-184°C to 340°C)

INCONEL® is a registered trademark of the Special Metals Corporation group of companies.

Elgiloy Specialty Metals - Wire Products
356 N.Cross Street
Sycamore, IL 60178 USA

Phone: 1 847 695 1900

WWW.ELGILOY.COM

REV 2024 04 02

LIMITATION OF LIABILITY AND DISCLAIMER OF WARRANTY:

The content in these data sheets is provided primarily by third-party melting mills and is provided for reference only. It is not intended for engineering or design.

Applications may be discussed, however, Elgiloy Specialty Metals does not recommend or endorse any material for any particular end use or application.

The data included in this data sheet are typical values and may vary.

Elgiloy Specialty Metals makes no representations or warranties, express or implied, as to the accuracy, completeness, condition, suitability, performance, fitness for a particular purpose, or merchantability of any information contained in any data sheet.

In no event will Elgiloy Specialty Metals be liable for any damages whatsoever arising from the use of the information included in the data sheets.