

Inconel® alloy 625

UNS N06625
W. Nr 2.4856

Applicable Specifications

Wire & Bar AMS 5666, AMS 5837, ASTM B446, AWS A5.14, NACE MR0175/ISO 15156-3, NACE MR0103/ISO 17945

Description: Inconel® 625 is a Nickel-Chromium-Molybdenum-Columbium (Niobium) alloy with excellent oxidation resistance, corrosion resistance, and strength at high temperatures. Age-hardening treatments are not required to obtain the high strength properties of Inconel® 625 due to the solid solution effects of molybdenum and columbium on the nickel-chromium matrix. Inconel® 625 is resistant to chloride-ion stress-corrosion cracking, pitting, and stress-corrosion cracking making it suitable for seawater applications. Inconel® 625 can operate from cryogenic temperatures up to 1800°F (980°C).

Applications include: Springs, seals, nuclear water reactors, and aircraft ducting systems.

Industries supplied include: Marine, Chemical Processing, and Aerospace.

Nominal Composition

| | Ni | Cr | Mo | Nb | Fe | Co | Si | Mn | Al | Ti | C |
|-----|----|----|----|------|----|-----|-----|-----|-----|-----|------|
| min | 58 | 20 | 8 | 3.15 | | | | | | | |
| max | | 23 | 10 | 4.15 | 5 | 1.0 | 0.5 | 0.5 | 0.4 | 0.4 | 0.10 |

Physical Properties

| | At 70°F | At 20°C |
|---------------------------|------------------------------------|---------------------------|
| Density | 0.305 lb/in ³ | 8.44 g/cm ³ |
| Modulus of Elasticity (E) | 30.1 x 10 ³ ksi | 208 GPa |
| Modulus of Rigidity (G) | 11.8 x 10 ³ ksi | 81.2 GPa |
| Coefficient of Expansion | 7.4 microinches/in.-°F (70-600°F) | 13.3 x μm/m-°C (20-300°C) |
| Electrical Resistivity | 50.8 μ ohm.in | 129 μ ohm.cm |
| Thermal Conductivity | 68 Btu-in./ft. ² hr.-°F | 9.8 W/m-K |

Typical Mechanical Properties

| Condition | Heat Treatment | Tensile Strength | Suggested Operating Conditions |
|---------------|---------------------------|----------------------------------|------------------------------------|
| Annealed | 1925-2050°F (1050-1120°C) | 120 – 150 ksi (830-1100 MPa) | -300°F to 1800°F (-184°C to 980°C) |
| Spring Temper | | 200 – 240 ksi (1380-1655 MPa) | -300°F to 700°F (-184°C to 370°C) |

INCONEL® is a registered trademark of the Special Metals Corporation group of companies.

Elgiloy Specialty Metals – Wire Products
356 North Cross Street
Sycamore, IL 60178 USA

Phone: 1-847-695-1900

www.elgiloy.com

REV 2024 04 02

LIMITATION OF LIABILITY AND DISCLAIMER OF WARRANTY:

The content in these data sheets is provided primarily by third-party melting mills and is provided for reference only. It is not intended for engineering or design.

Applications may be discussed, however, Elgiloy Specialty Metals does not recommend or endorse any material for any particular end use or application.

The data included in this data sheet are typical values and may vary.

Elgiloy Specialty Metals makes no representations or warranties, express or implied, as to the accuracy, completeness, condition, suitability, performance, fitness for a particular purpose, or merchantability of any information contained in any data sheet.

In no event will Elgiloy Specialty Metals be liable for any damages whatsoever arising from the use of the information included in the data sheets.