

Inconel® alloy X750

UNS N07750
W. Nr 2.4669

Inconel® X750 is a precipitation hardenable Nickel-Chromium alloy with high strength at temperatures up to 1300°F (704°C) and oxidation resistance up to 1800°F (982°C). Inconel® X750 offers excellent resistance to relaxation and as a result it is widely used for springs operating at elevated temperatures.

Applications include: springs operating from cryogenic temperatures up to 1300°F (704°C), fasteners and components requiring resistance to high temperature and corrosive environments.

Industries supplied include: Oil & Gas Extraction and Processing, Nuclear, Aerospace, Power Generation and Automotive

Nominal Composition

	Ni	Cr	Fe	Ti	Al	Cb (Nb)	Mn	Si	C	S	Cu
min	70.0	14.0	5.0	2.25	0.40	0.70	1.0				
max		17.0	9.0	2.75	1.0	1.20		0.50	0.08	0.01	0.5

Physical Properties

	At 70°F	At 1000°F	At 20°C	At 538°C
Density	0.299 lb/in ³		8.28 g/cm ³	
Modulus of Elasticity (E)	31.0 x 10 ⁶ psi	26.7 x 10 ⁶ psi	214 GPa	184 GPa
Modulus of Rigidity (G)	12.0 x 10 ⁶ psi		82.7 GPa	
Coefficient of Expansion	7.8 µin/in.-°F (70°F to 1000°F)		14.5 µm/m-°C (20°C to 538°C)	
Electrical Resistivity	20.1 µ ohm.in		122 µΩ.cm	
Thermal Conductivity	83 Btu-in/ft ² hr-°F		12.0 W/m-K	

Applicable Specifications

Wire & Bar | AMS 5698, AMS 5699, AMS 5778, NACE MR0175 (ISO 15156-3), ASTM B637, AMS 5667, AMS 5668, AMS 5670

Typical Mechanical Properties – Spring Applications

Condition	Heat Treatment	Tensile Strength	Suggested Operating Conditions
Annealed	2000 – 2200°F (1093 – 1204°C)	130 ksi max (896 MPa) max	
No.1 Temper	As supplied condition.	130 – 165 ksi (896 – 1138 MPa)	
No.1 Temper + Aged	After spring coiling. Age: 1350°F (732°C) for 16 hours.	165 – 220 ksi (1138 – 1517 MPa)	Optimum resistance to relaxation at temperatures up to 1000°F (538°C) with moderate or low stresses.
Spring Temper	As supplied condition.	160 – 220 ksi (1103 – 1517 MPa)	
Spring Temper + Aged	After spring coiling. Age: 1200°F (649°C) for 4 hours.	180 – 250 ksi (1241 – 1793 MPa)	Optimum stress and low relaxation at temperatures up to 700°F (371°C)
Spring Temper + Solution + Aged (3 Step Heat treatment)	After spring coiling. Solution Heat Treat: 2100°F (1149°C) for 2 hours and air cool. Age Harden at 1550°F (843°C) for 24 hours and air cool. Reheat to 1300°F (704°C) for 20 hours and air cool.	145 - 190 ksi (1000 – 1310 MPa)	Optimum resistance to relaxation at temperatures in the range 1000 – 1300°F (538 – 704°C).

INCONEL® is a registered trademark of the Special Metals Corporation group of companies.

Phone: 1 847 695 1900

Elgiloy Specialty Metals - Wire Products
356 N.Cross Street
Sycamore, IL 60178 USA

WWW.ELGILOY.COM

LIMITATION OF LIABILITY AND DISCLAIMER OF WARRANTY:

The content in these data sheets is provided primarily by third-party melting mills and is provided for reference only. It is not intended for engineering or design.

Applications may be discussed, however, Elgiloy Specialty Metals does not recommend or endorse any material for any particular end use or application.

The data included in this data sheet are typical values and may vary.

Elgiloy Specialty Metals makes no representations or warranties, express or implied, as to the accuracy, completeness, condition, suitability, performance, fitness for a particular purpose, or merchantability of any information contained in any data sheet.

In no event will Elgiloy Specialty Metals be liable for any damages whatsoever arising from the use of the information included in the data sheets.