

Nimonic® alloy 90

UNS N07090
W.Nr 2.4632, 2.4969

Nimonic® 90 is a precipitation hardenable Nickel-Chromium-Cobalt alloy with high strength at temperatures up to 1300°F (704°C) and creep and oxidation resistance up to 1688°F (920°C).

Applications include springs operating from ambient temperatures up to 1112°F (600°C), fasteners and components requiring resistance to high temperature and corrosive environments.

Industries supplied include: Oil & Gas Extraction and Processing, Nuclear, Aerospace, Power Generation and Automotive.

Nominal Composition

	Ni	Cr	Co	Fe	Ti	Al	Mn	Si	C
min		18.0	15.0		1.8	0.8			
max	Balance	21.0	21.0	3.0	3.0	2.0	1.0	1.5	0.13

Physical Properties

	At 70°F	At 1000°F	At 20°C	At 538°C
Density	0.296 lb/in ³		8.18 g/cm ³	
Modulus of Elasticity (E)	32.0 x 10 ⁶ psi	27.0 x 10 ⁶ psi	220 GPa	185 GPa
Modulus of Rigidity (G)	11.9 x 10 ³ psi		82.0 GPa	
Coefficient of Expansion	8.2 μ in/in-°F (70°F to 1000°F)		14.8 μm/m-°C (20°C to 538°C)	
Electrical Resistivity	46.5 μ ohm.in		118 μ ohm.cm	
Thermal Conductivity	80 Btu-in/ft ² hr-°F		11.5 W/m-K	

Applicable Specifications

Wire	AMS 5829, BS HR 501, BS HR 502, BS HR 503, BS 3075- NA19, NACE MR0175 / ISO 15156-3, NACE MR0103
------	--

Typical Mechanical Properties – Spring Applications

Condition	Heat Treatment	Tensile Strength	Suggested Operating Conditions
Solution Treated	1922 – 2012°F (1050 – 1100°C) + WQ	157 ksi max (1080 MPa) max	
Spring Temper	As supplied condition.	189 – 223 ksi (1300 - 1540 MPa)	
Spring Temper + Aged	After spring coiling. Age: 1202°F (650°C) for 4 hours. Alternatively, Age at 1112°F (600°C) for 16 hours and air cool.	189 – 260 ksi (1300 - 1800 MPa)	Optimum stress and low relaxation at temperatures up to 700°F (371°C)
Solution Treated + Aged	After Spring Coiling: Solution Heat Treat: 1976°F (1080°C) followed by rapid cooling + Age at 1382°F (750°C) for 4 hours and air cool. Alternatively, Age at 1292°F (700°C) for 16 hours and air cool.	145 - 203 ksi (1080 – 1400 MPa)	Optimum resistance to relaxation at temperatures up to 1112°F (600°C)

Nimonic® is a registered trade mark of the Special Metals Corporation group of companies.

Phone: 1 847 695 1900

Elgiloy Specialty Metals - Wire Products
356 N.Cross Street
Sycamore, IL 60178 USA

WWW.ELGILOY.COM

LIMITATION OF LIABILITY AND DISCLAIMER OF WARRANTY:

The content in these data sheets is provided primarily by third-party melting mills and is provided for reference only. It is not intended for engineering or design.

Applications may be discussed, however, Elgiloy Specialty Metals does not recommend or endorse any material for any particular end use or application.

The data included in this data sheet are typical values and may vary.

Elgiloy Specialty Metals makes no representations or warranties, express or implied, as to the accuracy, completeness, condition, suitability, performance, fitness for a particular purpose, or merchantability of any information contained in any data sheet.

In no event will Elgiloy Specialty Metals be liable for any damages whatsoever arising from the use of the information included in the data sheets.