

## Elgiloy Specialty Metals

### Alloy 301 Stainless Steel

UNS: S30100  
EN-DIN: 1.4310

Austenitic chromium-nickel stainless steel. Its high strength and corrosion resistance makes it a versatile alloy for a wide variety of applications. Typical applications include appliances, automotive applications, utensils, and high strength structural parts.

#### Nominal Composition

	C	Mn	P	S	Si	Cr	Ni	N	Fe		
min	-	-	-	-	-	16.0	6.0	-	-		
max	.15	2.0	0.045	0.030	1.00	18.0	8.0	0.10	BAL		

#### Physical Properties

	At 70°F	At 20°C
Density	0.285 lb./in <sup>3</sup>	7.88 g/cm <sup>3</sup>
Modulus of Elasticity (E)	28.0 x 10 <sup>3</sup> ksi	193 x 10 <sup>3</sup> MPa
Coefficient of Expansion	9.4 x 10 <sup>-6</sup> microinches/in.-°F (70-600°F)	16.9 μm/m-°C (20-300°C)
Electrical Resistivity	27.4 μ ohm.in	69.5 μ ohm.cm
Thermal Conductivity	9.4 Btu-in./ft. <sup>2</sup> hr.-°F	16.2 W/m-K

#### Applicable Specifications


ASTM A240, ASTM A666

#### Typical Mechanical Properties – Typical Room Temperature Mechanical Properties

Condition	Tensile Strength (UTS)*	0.2% YS*	Elongation% in 2" (50.8 mm)	Hardness Rockwell
Annealed	120 ksi ( 827 MPa)	45 ksi ( 310 MPa)	60	86 HRBW
¼ hard	125 ksi ( 862 MPa)	75 ksi ( 517 MPa)	25	25 HRCW
½ Hard	150 ksi ( 1034 MPa)	110 ksi (758 MPa)	18	32 HRCW
¾ Hard	175 ksi ( 1207 MPa)	135 ksi (931MPa)	12	37 HRCW
Full Hard	185 ksi ( 1276 MPa)	140 ksi (965MPa)	9	41 HRCW

Typical mechanical properties are based, AK source on ASTM A240/A666

\* Minimum- Standard practice is to produce to either minimum tensile strength, minimum yield or minimum hardness, but not to combinations of these properties. More Tempered Properties available upon request.



ELGILOY.COM

REV 2024 06 04

**LIMITATION OF LIABILITY AND DISCLAIMER OF WARRANTY:**

The content in these data sheets is provided primarily by third-party melting mills and is provided for reference only. It is not intended for engineering or design.

Applications may be discussed, however, Elgiloy Specialty Metals does not recommend or endorse any material for any particular end use or application.

In no event will Elgiloy Specialty Metals be liable for any damages whatsoever arising from the use of the information included in the data sheets.

The data included in this data sheet are typical values and may vary.

Elgiloy Specialty Metals makes no representations or warranties, express or implied, as to the accuracy, completeness, condition, suitability, performance, fitness for a particular purpose, or merchantability of any information contained in any data sheet.