

## **MATERIAL DATASHEET**

## **Alloy 305 Stainless Steel**

UNS: S30500 EN-DIN: 1.4303

Industries supplied include: appliances, kitchen utensils, tank covers, and other deep drawn parts. 305 grade stainless has similar corrosion resistance as 304 and has good oxidation resistance in air up to 1650 F (899 C). 305 can be readily formed and deep drawn into complex shapes due to its lower strength and work hardening rate and will remain nonmagnetic after cold work unlike 301 or 304. A caution is autogenous welds in 305 are more sensitive to hot cracking than 304 or 304L.

Nominal Composition											
	С	Mn	P	S	Si	Cr	Ni	N	Fe		
min	-	-	-	-	-	17.0	10.0	-	-		
max	.012	2.0	0.045	0.030	1.00	19.0	13.0	0.10	BAL		

Physical Properties					
	At 70°F	At 20°C			
Density	0.29 lb./in <sup>3</sup>	7.99 g/cm <sup>3</sup>			
Modulus of Elasticity (E)	28.0 x 10 <sup>3</sup> ksi in tension	193 x $10^3$ MPa in tension			
Coefficient of Expansion	$9.6 \times 10^{-6}$ microinches/in $^{\circ}$ F (32-212 $^{\circ}$ F)	17.3 μm/m-°C (0-100°C)			
Electrical Resistivity	28.4 μ ohm.in	72 μ ohm.cm			
Thermal Conductivity	9.4 Btu-in./ft. <sup>2</sup> hr°F (100°C)	16.2 W/m-K (100°C)			

## **Applicable Specifications**

AMS 5514, ASTM A240

ConditionTensile Strength (UTS)0.2% YSElongation% in 2" (50.8 mm)Hardness RockwellAnnealed85 ksi (586 MPa)35 ksi (241 MPa)5570 HRBW	Typical Mechanical Properties – Typical Room Temperature Mechanical Properties								
Annealed 85 ksi (586 MPa) 35 ksi (241 MPa) 55 70 HRBW	Condition	Tensile Strength (UTS)	0.2% YS	Elongation% in 2" (50.8 mm)	Hardness Rockwell				
	Annealed	85 ksi ( 586 MPa)	35 ksi ( 241 MPa)	55	70 HRBW				

Typical mechanical properties are based on AK source, ASTM A240



**ELGILOY.COM** 

## LIMITATION OF LIABILITY AND DISCLAIMER OF WARRANTY:

The content in these data sheets is provided primarily by third-party melting mills and is provided for reference only. It is not intended for engineering or design.

Applications may be discussed, however, Elgiloy Specialty Metals does not recommend or endorse any material for any particular end use or application.

The data included in this data sheet are typical values and may vary.

Elgiloy Specialty Metals makes no representations or warranties, express or implied, as to the accuracy, completeness, condition, suitability, performance, fitness for a particular purpose, or merchantability of any information contained in any data sheet.

In no event will Elgiloy Specialty Metals be liable for any damages whatsoever arising from the use of the information included in the data sheets.