

MATERIAL DATASHEET

Alloy 439 Stainless Steel

UNS: S43900
EN-DIN: 1.4510

439 Oxidation resistance and corrosion resistance is superior to Type 409 in areas where temperatures may exceed the oxidation limit of Type 409 or where aqueous corrosion resistance, particularly to chlorides, is needed. Applications include: Tubular manifolds and other exhaust system with difficult to form exhaust components.

Nominal Composition

	C	Mn	P	S	Si	Cr	Ni	Ti	Al	N	Fe
min	-	-	-	-	-	17.00	-	$\geq 0.20+4(C+N)$	-	-	-
max	.070	1.0	0.040	0.030	1.00	19.00	0.50	1.10	0.15	0.040	BAL

Physical Properties

	At 70°F	At 20°C
Density	0.278 lb./in ³	7685 kg/m ³
Modulus of Elasticity (E)	28.4 x 10 ³ ksi	193 x 10 ³ MPa
Electrical Resistivity	24.0 μ ohm.in	60.0 μ ohm.cm

Applicable Specifications

ASTM A240

Typical Mechanical Properties – Typical Room Temperature Mechanical Properties

Condition	Tensile Strength (UTS)	0.2% YS	Elongation% in 2" (50.8 mm)	Hardness Rockwell
Annealed	66 ksi (455 MPa)	43 ksi (296 MPa)	32	74 HRBW

Typical mechanical properties are based, AK source on ASTM A240



ELGILOY.COM

LIMITATION OF LIABILITY AND DISCLAIMER OF WARRANTY:

The content in these data sheets is provided primarily by third-party melting mills and is provided for reference only. It is not intended for engineering or design.

Applications may be discussed, however, Elgiloy Specialty Metals does not recommend or endorse any material for any particular end use or application.

In no event will Elgiloy Specialty Metals be liable for any damages whatsoever arising from the use of the information included in the data sheets.

The data included in this data sheet are typical values and may vary.

Elgiloy Specialty Metals makes no representations or warranties, express or implied, as to the accuracy, completeness, condition, suitability, performance, fitness for a particular purpose, or merchantability of any information contained in any data sheet.